



Paraoil. oil for you

PARAOIL INTERNATIONAL TRADING CO.,LTD.

White Petroleum Jelly Specificaiton

ITEMS	TEST METHOD	SPECIFICATION	TYPICAL VALUE
Colour Lovibond	IP-17	Max 1.5Y	0.3Y+0.0R
Drop Point, °C	IP-371	35-70	50
Cone Penetration @25°C, dmm	ASTM D937	160-180	166
Kinematic Viscosity @100°C, cst	ASTM D445	6.0-11.0	7.21
Description	BP New Edition	White,Translucent,Soft unctuous mass	White,Translucent,Soft unctuous mass
Odour Test	BP New Edition	Odourless	Odourless
Acidity / Alkalinity	BP New Edition	Complies with BP	Complies with BP
Sulphated Ash,%	BP New Edition	Complies with BP	Complies with BP
Light Absorbance @290nm,0.05%(w/v)	IP-2010	Complies with BP	Complies with BP
Organic foreign material	IP-2010	Complies with BP	Complies with BP